

AUTOTAK

Self-adhering water proofing membrane.

DESCRIPTION

AUTOTAK is a self-adhering waterproofing membrane made of distilled bitumen modified with SBS (styrene-butadiene-styrene) polymers, with an adhesive coating on the lower face and a self-protecting upper PE/ sand surface. The carrier is a composite polyester stabilised with longitudinal glass yarns that combines superior dimensional stability with good tensile strength, elongation values and excellent mechanical properties in general.

AVAILABLE SURFACE FINISHES

- Upper surface: Sand (AUTOTAK 2.0 mm) or plastic PE film (AUTOTAK 1.5 mm).
- Lower surface: silicone release film.

STORAGE

Store in a dry, cool place away from direct sunlight and frost.

USE FOR

AUTOTAK is recommended as underlayer in multilayer systems or as waterproofing layer below roof tiles or on pitched roofs in general where the use of a free flame is not permitted or advisable, thus preventing the use of a torch applied waterproofing membrane (i.e.: over wooden decks or fire sensitive insulation layers, etc.). **AUTOTAK** is fast and safe to apply and is a time saving product.

HEALTH AND SAFETY INFORMATION

- Ecology: According to local law.
- Transportation: Non hazardous.
- Toxic: Non toxic.

TECHNICAL INFORMATION

Properties	Test method	Unit	AUTOTAK 1.5mm	AUTOTAK 2.0 mm	TOL
Length	EN 1848-1	m	20,0 (-1%)	20,0 (-1%)	≥
Width	EN 1848-1	m	1,0 (-1%)	1,0 (-1%)	≥
Thickness	EN 1849-1	mm	1.5	2.0	± 5%
Tensile strength L/T (max load)	EN 12311-1	N/5cm	400/300	400/300	± 20%
Breaking elongation L/T	EN 12311-1	%	35/35	35/35	± 15
Resistance to tearing L/T	EN 12310-1	N	130/130	130/130	± 30%
Resistance to static loading	EN 12730 (A)	kg	10	10	≥
Impact resistance	EN 12691	mm	700	700	≥
Dimensional stability	EN 1107-1	%	± 0,3	± 0,3	≤
Flexibility at low temperature	EN 1109	°C	-15	-15	≤
Flow resistance at elevated temperature	EN 1110	°C	90	90	≥
Watertightness (A method)	EN 1928	kPa	60	60	≥
Water vapour transmission	EN 1931	μ	20.000	20.000	≥
Reaction to fire	EN 13501-1	Class	E	E	-
External fire exposure behaviour	EN 13501-5	Class	F roof	F roof	-

The information, and, in particular, the recommendations relating to the application and end-use of COPERNIT – distributed by VIETSTAR products, are given in good faith based on COPERNIT's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with COPERNIT's recommendation. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. COPERNIT reserves the right to change the properties of its products. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Imported by: VIETSTAR INDUSTRY COMPANY LIMITED
Head office: Sec.9, Duc Khe, Huong Son, My Duc, Hanoi, Vietnam
Factory: CN-1, Phu Nghia Industrial zone, Chuong My, Hanoi, Vietnam
Tel: +84. 24. 37880016 Email: contact@vietstarindustry.vn Website: vietstarindustry.vn
Produced by: Copernit - Italy

